

EGOSILICON 110 AQUARIUM

is a ready-to-use 1-component silicone sealant for the permanent sealing of glass elements, which vulcanizes via reaction with air humidity to form an elastic end product [free from fungicidal agents].

CHARACTERISTICS

The product is characterized by the following properties:

acidic cross-linking [acetoxyl] · free from fungicidal agents · good adhesion to glass · in accordance with DIN 32662 · weather, ageing & UV-resistant

APPLICATION AREAS

EGOSILICON 110 is suitable for professional bonding of frameless aquariums, glass constructions and similar applications.

Areas of application:

Frameless aquariums [DIN 32622] · Glass constructions · Showcases · Terrariums

Good adhesion to: [please note primer table]

Glass

Not or only partially suitable for: [Own tests assumed and recommended]

alkaline substrates [e.g. concrete] · black coatings · EPDM · non-ferrous metals · PE · PP · substrates containing bitumen, wax or kerosene · Teflon

APPLICATION NOTES

- ① Adhesion surfaces must be dry, load-bearing and free from dust and substances liable to impair adhesion.
- ② Clean with EGO REINIGUNGSSPRAY.*
- ③ In order to obtain optimum adhesion on suitable metals use Primer EGO PRIMER FML or EGO HAFTREINIGER (see Primer Chart).*
- * Notes:
 - Select cleaner depending on the substrate
 - Do not prime glass and glass-like surfaces
 - Own tests or consultation recommended.

STANDARDS AND TESTS

EGOSILICON 110 corresponds to the:

Standards according to:

- DIN EN 15651-2 G 25 LM CC
- DIN EN ISO 11600 G 25 HM
- DIN 32622, Abs. 4.4.2.2

IVD data sheets:

- No. 35

SUSTAINABILITY

VOC requirements:

- EMICODE EC1
- AgBB scheme
- french VOC class A+ and KMR regulation
- LEED® EQ c4.1

Quality mark:

- IVD-Industrieverband Dichtstoffe e.V. - tested by ift-Institut für Fensterertechnik e.V. Rosenheim

Environmental Product Declaration (EPD):

- Sample-EPD (Silicone-based products, group 2)

QNG/Quality seal for sustainable buildings:

- Adhesives and sealants for creating the airtightness of the facade in accordance with BNB_BN_1.1.6, Annex 1, item 9 + QNG-313, item 4.3
- Adhesives and sealants in interiors incl. TGA according to BNB_BN_1.1.6, Annex 1, Item 8 + QNG-313, Items 4.1, 4.2



*Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions)

TECHNICAL DATA

Specifications	Results	In accordance with
Cross-linking system	Acidic (Acetoxy)	
Density	approx. 1,0 g/cm ³	DIN EN ISO 1183-1
Application temperature	from +5 °C to +40 °C	
Temperature resistance	-60 °C to +180 °C	
Shore A hardness	approx. 25	DIN EN ISO 868
Spray-out behavior	approx. 140g/min (6mm; 3bar)	DIN EN ISO 8394-1
Modulus / tensile stress 100%	approx. 0,5 N/mm ²	DIN EN ISO 8339
Volume shrinkage	< 5 %	DIN EN ISO 10563
Resilience	approx. 100 %	DIN EN ISO 7389
Allowable total deformation	25 %	
Viscosity	stable	DIN EN ISO 7390
Skin formation time	approx. 10-20 Minuten (23 °C/50% RH)	
Vulcanization	approx. 3 mm/24 hours	
Ignition temperature	approx. 450 °C	DIN 51794
Building material class	B2, normal flammability Euroclass E	DIN 4102 DIN EN 13501

AVAILABILITY AND STORAGE

Colors	transparent, black [see color chart]
Packaging	<ul style="list-style-type: none"> ■ 310 ml cartridges [20 pieces/carton, 60 cartons/pallet] ■ Special containers on request
Storage	<p>Can be stored in its original packaging in a cool, dry place (+15 to +25 °C, relative humidity < 60 °C):</p> <ul style="list-style-type: none"> ■ 18 months <p>The production or best-before date can be found on the container label.</p>

SAFETY INSTRUCTIONS

Complies with	Regulation (EC) No 1907/2006 (REACH)
Not hazardous according to	Regulation (EC) No 1272/2008 (CLP)
Not subject to labeling according to	Regulation (EC) No 1272/2008 (CLP)
Safety instructions	see SDS
Disposal instructions	see SDS

For warnings see EC safety data sheet. The above information is the result of thorough research; previous information is hereby invalidated. Check for yourself whether the product is suitable for your purposes. Our possible liability is limited to the value of our product as such. We cannot accept any liability for indirect damage, in particular for the use or unusability of the product. No one is authorized to make recommendations or assurances on our behalf that go beyond the content of our information sheets.