

## EGO SB 11

### TYPICAL USES

is a softplastic putty

For single glazing in timber and metal windows and their combinations according to groups 1 to 3 of RoTa chart (determination of stress groups for glazing windows) worked out by the Institut für Fenstertechnik e. V., Rosenheim or of DIN 18545.

### APPLICATION

Apply **EGO SB 11** only onto dry and clean profiles that are free from substances liable to impair adhesion. Timber frames (moisture max. 15 %) must be painted prior to the application. Apply **EGO SB 11** in sufficient quantity and without bubbles.



Meets Requirements of DIN 18545-B

### PLEASE OBSERVE

DIN 18361 (Glazing work)

DIN 18545 (Sealing of glazing with sealants)

DIN 18363 (Paintwork)

ÖNORM B3722 (Glass in building – Requirements for sealings of glazing rebates and glazing systems with sealants)

Technical directives for window paints

Instructions 18 by Bundesausschuss Farbe and Sachwertschutz

In case of profiles made of galvanised steel, non-ferrous metal and marble please contact us.

### TECHNICAL DATA

Properties	Result
Density	approx. 2 g/cm <sup>3</sup>
Application Temperature	+ 5° C to + 30° C
Service Temperature	approx. - 30° C to + 80° C
Consistency	softplastic
Properties	hardening, non-shrinking
Method of Application	manually or with <b>EGOFIX</b> Compressed Air Gun
Rework	with polished putty knife, clear smoothing
Secondary Treatment	Smooth carefully with a polished putty knife Over-paint all putty surface with a weatherproof paint at the earliest after skin formation, at the latest after 8 weeks.

## AVAILABILITY AND STORAGE

Standard Colour	grey
Packaging	5 kg bucket 10 kg bucket 25 kg bucket
Storage	Store in cool and dry conditions in closed original packaging. Shelf life 12 months

## SAFETY INSTRUCTIONS

Meets Requirements of	REACH Regulation (EC) No. 1907/2006
Not hazardous	According to EC No. 1272/2008 (CLP)
Not subject to Labelling	According to EC No. 1272/2008 (CLP)
Safety Guidelines	See EC safety data sheet
Disposal	See EC safety data sheet