

EGO SB 25

TYPICAL USES

APPLICATION

is a softplastic putty.

For single glazing in timber and metal windows and their combinations according to stress groups 1 to 5 of RoTa chart (determination of stress groups for glazing windows) worked out by the Institut für Fenstertechnik e. V., Rosenheim or of DIN 18545.

Apply **EGO** SB **25** only onto dry and clean profiles that are free from substances liable to impair adhesion. Timber frames (moisture max. 15 %) must be painted prior to the application. Apply **EGO** SB **25** in sufficient quantity and without bubbles.



Meets Requirements of DIN 18545-B

PLEASE OBSERVE

DIN 18361 (Glazing work)

DIN 18545 (Sealing of glazing with sealants)

DIN 18363 (Paintwork)

ÖNORM B3722 (Glass in building – Requirements for sealings of glazing rebates and glazing systems with sealants)


Technical directives for window paints

Instructions 18 by Bundesausschuss Farbe and Sachwertschutz

In case of profiles made of galvanised steel, non-ferrous metal and marble please contact us.

TECHNICAL DATA

Properties	Result
Density	approx. 2 g/cm ³
Application Temperature	+ 5° C to + 30° C
Service Temperature	approx 30° C to + 80° C
Consistency	softplastic, thixotropic
Properties	non-shrinking
Method of Application	manually or with EGO FIX Compressed Air Gun
Rework	with polished putty knife, clear smoothing
Secondary Treatment	Smooth carefully with a polished putty knife Overpaint all putty surface with a weatherproof paint at the earliest after skin formation, at the latest after 8 weeks.







ISO 14001:2015



EGO Dichtstoffwerke GmbH & Co. Betriebs KG • Kaltenbrunn 27 • D-82467 Garmisch-Partenkirchen



AVAILABILITY AND STORAGE

Standard Colour

Packaging

10 kg bucket

25 kg bucket

50 mm Ø sausages, 15 kg/box

70 mm Ø sausages, 15 kg/box

Special packaging upon request.


Storage

Store in cool and dry conditions in closed original packaging. Shelf life 12 months

SAFETY INSTRUCTIONS

Meets Requirements of	REACH Regulation (EC) No. 1907/2006
Not hazardous	According to EC No. 1272/2008 (CLP)
Not subject to Labelling	According to EC No. 1272/2008 (CLP)
Safety Guidelines	See EC safety data sheet
Disposal	See EC safety data sheet

Precautions see EC Security Data Sheet. The above specifications are the result of careful research and development. All previous specifications are hereby null and void. Users are them selves responsible for ensuring the suitability of the product for the purpose intended, liability on the part of EGO being limited to the purchase price of the material. EGO cannot accept liability for damage, in particular that caused by the use of the product or its unsuitability, nor can EGO accept responsibility for unauthorized recommendations or guarantees which deviate from or exceed the specifications given in this product data sheet.









EGO Dichtstoffwerke GmbH & Co. Betriebs KG • Kaltenbrunn 27 • D-82467 Garmisch-Partenkirchen