

Type	Curing system	Shore A hardness DIN 53505	Module/ tensile stress 100 % DIN EN ISO 8339	acc. total deformation	Class after DIN EN 15651 or DIN EN SIO 11600
EGOSILICONE 100 ORIGINAL	acidic (acetoxo)	approx. 20	approx. 0.4 N/mm <sup>2</sup>	25.0%	F 25 LM EXT-INT-CC G 25 LM CC
EGOSILICONE 110 AQUARIUM	acidic (acetoxo)	approx. 25	approx. 0.5 N/mm <sup>2</sup>	25.0%	G 25 HM
EGOSILICONE 111 FOOD & DRINKING WATER	acidic (acetoxo)	approx. 25	approx. 0.6 N/mm <sup>2</sup>	20.0%	F 20 HM EXT-INT-CC G 20 HM CC
EGOSILICONE 120 HIGH TEMPERATURE	acidic (acetoxo)	approx. 32	approx. 0.7 N/mm <sup>2</sup>	20.0%	F 20 HM EXT-INT-CC G 20 HM CC
EGOSILICONE 151 SANITARY PROFESSIONAL	acidic (acetoxo)	approx. 20	approx. 0.4 N/mm <sup>2</sup>	25.0%	F 25 LM EXT-INT-CC G 25 LM CC XS 1
EGOSILICONE 191 SANITARY SEAL	acidic (acetoxo)	approx. 30	approx. 0.6 N/mm <sup>2</sup>	25.0%	XS 1
EGOSILICONE 300 CONSTRUCTION SEALANT	neutral (oxim)	approx. 25	approx. 0.4 N/mm <sup>2</sup>	25.0%	F 25 LM EXT-INT-CC G 25 LM CC
EGOSILICONE 310 FIRE PROTECTION B1	neutral (oxim)	approx. 25	approx. 0.4 N/mm <sup>2</sup>	25.0%	F 25 LM EXT-INT-CC G 25 LM CC
EGOSILICON 333 GLAZED FACADE	neutral (oxim)	approx. 33	approx. 0,6 N/mm <sup>2</sup>	20,0 %	F 20 HM EXT-INT-CC G 20 HM CC
EGOSILICONE 351 NATURAL STONE	neutral (oxim)	approx. 24	approx. 0.5 N/mm <sup>2</sup>	20.0%	F20HM EXT-INT XS 1
EGOSILICONE 351 NATURAL STONE, MATT	neutral (oxim)	approx. 31	approx. 0.5 N/mm <sup>2</sup>	20.0%	F20HM EXT-INT XS 1
EGOSILICONE 352 NATURAL STONE, TEXTURED	neutral (oxim)	approx. 24	approx. 0.4 N/mm <sup>2</sup>	25.0%	F 25 LM EXT-INT-CC G 25 LM CC XS 1
EGOSILICONE 360 THE BUILDING EXPERT	neutral (oxim)	approx. 20	approx. 0.4 N/mm <sup>2</sup>	25.0%	F 25 LM EXT-INT-CC G 25 LM CC
EGOSILICONE 365 ALL IN ONE	neutral (oxim)	approx. 24	approx. 0.4 N/mm <sup>2</sup>	25.0%	F 25 LM EXT-INT-CC G 25 LM CC XS 1
EGOSILICONE 365 MATT	neutral (oxim)	approx. 31	approx. 0.4 N/mm <sup>2</sup>	25.0%	F 25 LM EXT-INT-CC G 25 LM CC XS 1
EGOSILICONE 460 BAUFIX	neutral (alkoxy)	approx. 24	approx. 0.4 N/mm <sup>2</sup>	25.0%	F 25 LM EXT-INT-CC G 25 LM CC
MIRROR ADHESIVE PAINTED GLASS ADHESIVE	neutral (alkoxy)	approx. 25	approx. 0.5 N/mm <sup>2</sup>	20.0%	