

## EGOSILICON 310 FIRE PROTECTION

is a ready-to-use, tested, high-quality 1-component silicone sealant that vulcanizes into an elastic end product via reaction with atmospheric moisture.

### CHARACTERISTICS

The product is characterized by the following properties:

neutral cross-linking [Oxim] · flame-retardant · no smoke · no burning fall-off/dripping · fungicide · weather, ageing & UV-resistant

### APPLICATION AREAS

EGOSILICON 310 is suitable for sealing fire-retardant and fire-resistant glazing and connection seals. Tested as flame-retardant [B1 according to DIN 4102 and the best Euroclass B-s1, d0 according to DIN EN 13501-1 and the Swiss VKF fire classification number BKZ 5.3].

**Areas of application:**

Fire protection · Facade · Transportation · Electrical engineering

**Good adhesion to:** [please note primer table]

Glass · Concrete · Metal

**Not or only conditionally suitable on:** [own tests assumed and recommended]

Non-ferrous metals · EPDM · PE · PP · Black coatings · Teflon · Substrates containing bitumen, wax and kerosene

### APPLICATION NOTES

- ① Clean the bonding surfaces with **EGO CLEANER**®.
  - ② The bonding surfaces must be clean, dry, stable and free of dust and release agents.
  - ③ Pre-treatment according to **EGO PRIMER** recommendations®.
  - ④ Process indoors with good ventilation and then continue to ventilate well.
  - ⑤ Use **EGO SMOOTHING AGENT** for post-treatment.
- \* Notes:
- Select cleaner depending on the substrate.
  - Do not prime glass and glass-like surfaces.
  - Own tests or consultation recommended.

### STANDARDS AND TESTS

EGOSILICON 300 corresponds to the:

**Standards according to:**

- DIN 18540
- DIN EN ISO 11600 F 25 LM
- DIN EN ISO 11600 G 25 LM
- DIN EN 15651-1 F 25 LM EXT-INT-CC
- DIN EN 15651-2 G 25 LM CC
- DIN 52452-4 A1 compatible with paint

**IVD data sheets:**

- Nr. 11, 19-1, 24, 29, 31, 35

The following tests were achieved by EGOSILICON 310:

**European conformity:**

- CE marking Declaration of Performance LE/DoP No. EG03310314

**Test certificate:**

- for proof of fire behavior according to DIN 4102 Part 1

**Classification report:**

- on the fire behavior of building products according to DIN EN ISO 11925-2 (DIN EN 13501-1)

**Fire index:**

- BKZ 5.3 (low flammability / low quality)

**Test according to:**

- „Guidelines for fire police regulations: Building materials and components“ of the Association of Cantonal Fire Insurers (VKF)

### SUSTAINABILITY

**VOC requirements:**

- AgBB scheme
- French VOC class A+ and KMR regulation
- LEED® EQ c4.1

**Seal of quality:**

- IVD-Industrieverband Dichtstoffe e.V. - tested by ift-Institut für Fenstertechnik e.V. Rosenheim

## EGOSILICON 310 FIRE PROTECTION

### SUSTAINABILITY

#### Environmental Product Declaration (EPD):

- Sample EPD (Silicone-based products, group 1)



\*Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions)

### TECHNICAL DATA

Specifications	Results	In accordance with
Cross-linking system	neutral (Oxime)	
Density	approx. 1,4 g/cm <sup>3</sup>	DIN EN ISO 1183-1
Application temperature	from +5 °C to +40 °C	
Temperature resistance	-60 °C to +150 °C	
Shore A hardness	approx. 25	DIN EN ISO 868
Spray-out behavior	approx. 280g/min (6mm; 3bar)	DIN EN ISO 8394-1
Modulus / tensile stress 100%	approx. 0,4 N/mm <sup>2</sup>	DIN EN ISO 8339
Volume shrinkage	< 10%	DIN EN ISO 10563
Resilience	approx. 100 %	DIN EN ISO 7389
Allowable total deformation	25%	
Viscosity	stable	DIN EN ISO 7390
Skin formation time	approx. 15-30 minutes (23 °C/50% rel. LF)	
Vulcanization	approx. 2 mm/24 hours	
Ignition temperature	approx. 450 °C	DIN 51794
Building material class	B1, flame retardant B-s1, d0 flame retardant, no smoke, no burning droplets/droplets	DIN 4102 DIN EN 13501

### AVAILABILITY AND STORAGE

Colors	white, manhattan, anthracite [see color chart]
Packaging	<ul style="list-style-type: none"> <li>310 ml cartridges (20 pieces/carton, 60 cartons/pallet)</li> <li>Special containers on request</li> </ul>
Storage	Can be stored cool and dry in original packaging: <ul style="list-style-type: none"> <li>18 months [cartridges]</li> <li>24 months [foil bags]</li> </ul> Das Produktions- oder Mindesthaltbarkeitsdatum entnehmen Sie dem Gebindeaufdruck.

### SAFETY INSTRUCTIONS

Complies with	Regulation (EC) No 1907/2006 (REACH)
Not hazardous according to	Regulation (EC) No 1272/2008 (CLP)
Not subject to labeling according to	Regulation (EC) No 1272/2008 (CLP)
Safety instructions	see SDS
Disposal instructions	see SDS

For warnings see EC safety data sheet. The above information is the result of thorough research; previous information is hereby invalidated. Check for yourself whether the product is suitable for your purposes. Our possible liability is limited to the value of our product as such. We cannot accept any liability for indirect damage, in particular for the use or unusability of the product. No one is authorized to make recommendations or assurances on our behalf that go beyond the content of our information sheets.