

# EGOSIT

## TYPICAL USES

is a viscoplastic putty.

For single and double glazing in timber and metal windows and their combinations according to stress groups 1 to 5 of RoTa chart (determination of stress groups for glazing windows) worked out by the Institut für Fenstertechnik e. V., Rosenheim or of DIN 18545. **EGOSIT** is resistant to wind pressure of up to 720 g/ cm<sup>2</sup> glass surface.

## APPLICATION

Apply **EGOSIT** only onto dry and clean profiles that are free from substances liable to impair adhesion. Timber frames (moisture max. 15 %) must be painted prior to the application. Apply **EGOSIT** in sufficient quantity and without bubbles.



Meets Requirements of DIN 18545-B

## PLEASE OBSERVE

- DIN 18361 (Glazing work)
- DIN 18545 (Sealing of glazing with sealants)
- DIN 18363 (Paintwork)
- ÖNORM B3722 (Glass in building – Requirements for sealings of glazing rebates and glazing systems with sealants)
- Technical directives for window paints
- Instructions 18 by Bundesausschuss Farbe and Sachwertschutz
- In case of profiles made of galvanised steel, non-ferrous metal and marble please contact us.

## TECHNICAL DATA

Properties	Result	In accordance with
Density	approx. 2 g/cm <sup>3</sup>	DIN EN ISO 10563
Application Temperature	+ 5° C to + 30° C	
Service Temperature	approx. - 30° C to + 80° C	
Consistency	viscoplastic, thixotropic	
Properties	hardening, non-shrinking	
Method of Application	manually or with <b>EGOFIX</b> Compressed Air Gun	
Rework	with polished putty knife, clear smoothing	
Secondary Treatment	Smooth carefully with a polished putty knife. Over-paint all putty surface with a weatherproof paint at the earliest after skin formation, at the latest after 8 weeks.	

**AVAILABILITY AND STORAGE**

Standard Colour	Grey, white
Standard Dimensions	10 kg bucket 25 kg bucket 70 mm Ø foil bags, 15 kg/box Special packaging upon requested.
Storage	Store in cool and dry conditions in closed original packaging. Shelf life 12 months

**SAFETY INSTRUCTIONS**

Meets Requirements of	REACH Regulation (EC) No. 1907/2006 and No. 1272/2008 CLP
Labelling	See EC safety data sheet
Safety Guidelines	See EC safety data sheet
Disposal	See EC safety data sheet

Precautions see EC Security Data Sheet. The above specifications are the result of careful research and development. All previous specifications are hereby null and void. Users are them selves responsible for ensuring the suitability of the product for the purpose intended, liability on the part of EGO being limited to the purchase price of the material. EGO cannot accept liability for damage, in particular that caused by the use of the product or its unsuitability, nor can EGO accept responsibility for unauthorized recommendations or guarantees which deviate from or exceed the specifications given in this product data sheet.

