

## EGOSIT GLASS PUTTY

is a viscoplastic putty.

### APPLICATION AREAS

EGO VERSTREICHKIT is suitable for single and double glazing in timber and metal windows and their combinations according to stress groups 1 to 5 of RoTa chart (determination of stress groups for glazing windows) worked out by the Institut für Fenstertechnik e. V., Rosenheim or of DIN 18545. EGOSIT is resistant to wind pressure of up to 720 g/ cm<sup>2</sup> glass surface.

#### Anwendungsgebiete:

Single & insulating glazing · window frames

#### Good adhesion to:

wood · metal

### APPLICATION NOTES

- ① Apply EGOSIT only onto dry and clean profiles that are free from substances liable to impair adhesion.
- ② Timber frames (moisture max. 15 %) must be painted prior to the application.
- ③ Apply EGOSIT in sufficient quantity and without bubbles.

### NORMS AND TESTS

#### EGOSIT complies with the standards:

- DIN 18361 (Glazing work)
- DIN 18545 (Sealing of glazing with sealants)
- DIN 18363 (Paintwork)
- ÖNORM B3722 (Glass in building – Requirements for sealings of glazing rebates and glazing systems with sealants)

#### Technical directives for window paints:

- Instructions 18 by Bundesausschuss Farbe und Sachwertschutz
- In case of profiles made of galvanised steel, non-ferrous metal and marble please contact us.

### TECHNICAL DATA

Properties	Result
Density	approx. 2 g/cm <sup>3</sup> [in accordance with DIN EN ISO 10563]
Application Temperature	approx. +5 °C to +30 °C
Service Temperature	approx. -30 °C to +80 °C
Consistency	viscoplastic, thixotropic
Properties	hardening, non-shrinking
Method of Application	manually or with EGOFIX Compressed Air Gun
Rework	with polished putty knife, clear smoothing
Secondary Treatment	Smooth carefully with a polished putty knife. Overpaint all putty surface with a weather-proof paint at the earliest after skin formation, at the latest after 8 weeks.

### AVAILABILITY AND STORAGE

Standard Colour	grey
Standard Dimensions	<ul style="list-style-type: none"> <li>▪ 10 kg plastic bucket</li> <li>▪ 25 kg plastic bucket</li> <li>▪ 25 kg tin bucket</li> <li>▪ 70 mm Ø foil bags, 15 kg/box</li> <li>▪ Special packaging upon requested.</li> </ul>
Storage	Store in original packaging in a cool, dry place: <ul style="list-style-type: none"> <li>▪ 12 months</li> </ul>

### SAFETY INSTRUCTIONS

Meets Requirements of	REACH Regulation (EC) No. 1907/2006 and No. 1272/2008 CLP
Labelling	See EC safety data sheet
Safety Guidelines	See EC safety data sheet
Disposal	See EC safety data sheet

For warnings refer to the Safety Data Sheet. The above information is the result of thorough research; previous information is hereby invalidated. Check for yourself whether the product is suitable for your purposes. Our possible liability is limited to the value of our product as such. We cannot accept any liability for indirect damage, in particular for the application or unusability of the product. No one is authorized to make recommendations or assurances on our behalf that go beyond the content of our information sheets.