

Primer-Anwendungstabelle	BUTYL	SILICON			HYBRID	PUR	ACRYL
	EGOBON EGOFERM EGOPOL Serie	EGOSILICON 100er Serie (Acetat)	EGOSILICON 300er Serie (Oxim)	EGOSILICON 400er Serie (Alkoxy)	EGO HYBRID Serie (SMP)	EGOFLEX Serie	EGOCRYL Serie
Acrylglas (PMMA)	✓	*	FML*/HR	FML*/HR/✓	✓/***	✗	✗
Acryllack	✓	FML/✓	FML/✓**	FML/✓/***	✓/***	✓/HR	✓
Alkydharzlack	✓	✓	✓**	✓/***	✓/***	HR	✓
Aluminium blank	✓	FML/***	FML/***	FML/***	HR/✓/***	***	✗
Aluminium eloxiert	✓	FML/✓	FML/✓	FML/✓	HR/✓/***	HR	✗
Beton	PRO/ECO	✗	FWS/FDF	FDF/✓/***	FDF/✓/***	PUR	vAc
Bitumen	PRO	✗	✗	✗	✗	✗	✗
Blei	✓/PRO	✗	FML	FML/***	HR/***	HR/***	✗
Chrom	✓	✗	FML	FML/***	✓/HR/***	✗	✗
DD-Lack	✓	✓	✓**	✓/***	✓/***	✓/HR	✓
Dispersionsfensterlack	✓	FML/✓	✓**	✓/***	✓/***	✓/HR	✓
Dispersionsfassadenfarbe	✓	✗	FML/FDF/***	FML/FDF/***	✓	✓/HR	✓
Edelstahl (V2A) (V4A)	✓	FML/HR	FML/HR	FML/HR/✓	HR/✓/***	HR	✗
Eisen	✓/PRO	✗	FML	FML/***	HR/***	HR	✗
Emaile	✓	✓	✓	✓	✓	HR	✗
Epoxidharzlack	✓	✓	✓	✓/***	✓	✓/HR	✗
Faserzement	PRO/ECO	✗	FWS	FWS/***	FDF/***	PUR	vAc
Fliesen glasiert	✓	✓	✓	✓	✓	HR	✗
Fliesen unglasiert	✓/PRO/ECO	✗	FWS/FDF	FWS/FDF/***	✓	PUR	✓
Glas	✓	✓	✓	✓	✓	✗	✗
Kunststein	✓	✗	FDF/***	✗	✓/***	✓/HR/***	✓/ vAc
Kupfer	✓	✗	FML**	FML/✓/***	✗	HR/***	✗
Lasuranstrich	✓	FWS/FML	FML/✓	FML/✓/***	✓	✓/HR	✓
Melaminharz	✓	FWS/HR/✓	FWS/HR/✓	FWS/HR/✓/***	HR/✓/***	HR	✓
Messing	✓	✗	FML**	FML/***	HR/***	HR/***	✗
Naturstein	✗	✗	FDF/***	✗	FDF/***	✓/HR/***	✗
Polycarbonat (PC)	✓	FML*/HR	FML*/HR	FML*/HR/✓/***	✓/***	✗	✗
Polyester (GFK)	✓	FML/HR	FML/HR	FML/HR/***	✓/***	HR	✗
Porenbeton	PRO/ECO	✗	FWS/FDF	FWS/FDF/***	FDF/***	PUR	vAc
Pulverlackbeschichtung	✓	FML/HR	FML/HR	FML/HR/***	HR/✓/***	HR	✗
PVC hart	✓	FWS/FML	FWS/FML	FWS/FML/✓/***	✓/***	PUR	✗
Stahl blank	✓	✗	FML	FML/***	HR/✓/***	HR	✗
Stahl verzinkt	✓	✗	FML	FML/***	HR/✓/***	HR	✗
Styropor	✓/ECO	✗	✓	✓/***	✓/***	✗	✓
Zinkblech	✓	✗	FML	FML/***	HR/***	HR	✗
Zinkstaubfarbe	✓	✗	FML	FML/***	✓/***	HR/***	✓

✓ = Anwendung ohne Primer möglich

✗ = Anwendung nicht empfohlen

\* = Primer dünn auftragen und für schnelle Ablüftung sorgen da bei Langzeiteinwirkung die Gefahr von Spannungsriss Korrosion besteht.

\*\* = Spaltprodukte gut ablüften lassen

\*\*\* = Eigenversuche werden empfohlen

FDF = EGO PRIMER FDF

FML = EGO PRIMER FML

PUR = EGO PRIMER PUR

HR = EGO HAFTREINIGER

PRO = EGO BUTYLPRIMER PRO (lösemittelhaltig)

ECO = EGO BUTYLPRIMER ECO (lösemittelfrei)

vAc = mit Wasserverdünntes EGOCRYL