Туре	Density	Hardness Shore A	Acc. total deformation	Skin formation time
EGOCRYL 500 Maleracryl	approx. 1,6 g/cm ³	approx. 15	12,5 %	approx. 15 Min
EGOCRYL 530 Maleracryl	approx. 1,6 g/cm ³	approx. 15	12,5 %	approx. 15 – 30 Min.
EGOPLAST FK Folienkleber	approx. 1,0 g/cm³	-	-	approx. 30 Min.