

Type	Density	Handling temperature	Temperature resistance	Shore A hardness	Module/tensile stress	Acc. total deformation	Zu Bruchdehnung	Viscosity	Skin formation time	Hardening time/ complete vulcanisation	Resilience	Standard colours
EGOFLEX 423 FLOOR AND CONNECTION JOINTS	approx. 1.3 g/cm ³	+5 °C to +40 °C	-40 °C to +80 °C	approx. 40	0.6 N/mm ² at 100% (DIN EN ISO 8339)	25 %	800%	stable	approx. 65 minutes	3 mm/ 24 hrs	> 90 %	concrete grey