

Type	Raw material basis	Mixing ratio	Colour	Pot life	Early strength	Processing time	Final strength
EGOPOXID 2000 RAPID	Epoxy resin	1 : 1	milky transparent and black	approx. 5 – 10 minutes (20 g formulation)	approx. 45 minutes	approx. 12 hours	approx. 48 hours
EGOPOXID 2100 PUTTY	Epoxy resin	2 : 1	milky	approx. 30 – 40 minutes (30 g formulation)	approx. 4 hours	approx. 12 hours	approx. 48 hours
EGOPOXID 3000 RAPID EXTRA	Epoxy resin	1 : 1	milky transparent	approx. 3 – 5 minutes (20 g formulation)	approx. 30 min	approx. 12 hours	approx. 48 hours